




PLANK HARDWOOD FLOORING | TECHNICAL INFORMATION

Product # 1154-1842-10



WHITE BREATHE COLLECTION DECOR | AQUA WHITE

Wood species | Oak
Selection | Select & Better
Constructions | 3-layer flooring T&G
Size | 19,05x127x600...2100 mm (3/4"x5"x2'...7")
Finish | Silk mat finish

CONSTRUCTION: 3-LAYER FLOORING T&G

| DIMENSIONS : | | | PACKAGING : | |
|----------------|----------------------|-----------|---------------------|-----------------------------|
| | | | BOX | PALLET |
| Thickness | 19,05 mm (3/4") | Content | 2 m ² | 36 box (72 m ²) |
| Width | 127 mm (5") | Weigh | 25 kg | 917 kg |
| Length | 600...2100 (2'...7') | H x W x L | 90 x 275 x 2 155 mm | 1156 x 846 x 2 163 mm |
| Average length | 0.98 m (3 1/4') | Content | 21,520 sq.ft. | 774,720 sq.ft. |
| Microlevel | 0,5 mm | Weigh | 26 lb | 929 lb |
| Joint type | T&G | H x W x L | 4" x 11" x 85" mm | 46" x 33" x 86" mm |

DEVIATIONS:

| | | |
|------------------------|---------------------------|------------------------|
| Deviation on Thickness | ± 0,2 mm | EN 13489 ГОСТ 862.3 |
| Deviation on Width | ± 0,2 mm | |
| Height Difference | ≤ 0,2 mm on 100 mm length | |
| Cup | ≤ 0,2 % of width | EN 13489 |
| Bow | ≤ 0,5 % of length | |
| Spring | ≤ 0,1 % of length | |

CHARACTERISTICS:

| | | |
|-----------------------------|---------------------------|----------|
| Fire resistance | Dfl-s1 | EN 14342 |
| Formaldehyde emission class | E1 | |
| Pentachlorophenol content | None | |
| Thermal resistance | 0,082 m ² ·K/W | |
| Thermal conductivity | 0,161 W/(m·K) | |
| Structural warranty | Lifetime | |

УСТАНОВКА:



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

УСЛОВИЯ ЭКСПЛУАТАЦИИ И ХРАНЕНИЯ:



— Air humidity 40% – 65%
— Temperature +18 °C – +22 °C

FINISH : SILK MAT FINISH

GRADE : SELECT & BETTER

| DESCRIPTION: | | DESCRIPTION: | |
|------------------|------------------------------------------------------------|----------------|--------------------------------------------------------------|
| Sound sapwood | Non-contrasting sapwood is allowed up to 25% of plank area | Bark pocket | Permitted up to 10 mm in length, up to 3 mm in width, filled |
| Colour variation | Permitted slight colour variation | Pith | Permitted healthy heart |
| Knot | Permitted up to 10 mm, filled | Slope of grain | Permitted |
| Crecks | Not permitted | Medullary ray | Permitted |

COSWICK Ltd.

2B Kolasa Str., 223034 Zaslavl, Republic of Belarus
Tel.: +375-17-543-2012, Fax: +375-17-543-2020, E-mail: sales@coswick.com
www.coswick.com

