




# MOSAIC WOOD FLOORS FLOORS | TECHNICAL INFORMATION

Product # 1150-1829-10



## DARK WOOD COLLECTION DECOR | BROWN SUGAR

**Wood species** | Oak  
**Selection** | Select & Better  
**Pattern** | Coffee Bean  
**Constructions** | 3-layer flooring T&G  
**Size** | 19,05x127x433,8 mm (3/4"x5"x17 1/16")  
**Finish** | Silk mat finish

### CONSTRUCTION: 3-LAYER FLOORING T&G

| DIMENSIONS :   |                  |           | PACKAGING :        |                       |
|----------------|------------------|-----------|--------------------|-----------------------|
|                |                  |           | BOX                | PALLET                |
| Thickness      | 19,05 mm (3/4")  | Content   | 1,38 m2            | 40 box (55,2 m2)      |
| Width          | 127 mm (5")      | Weigh     | 17 kg              | 702 kg                |
| Length         | 433,8 (17 1/16") | H x W x L | 195 x 405 x 575 mm | 1091 x 800 x 2 000 mm |
| Average length |                  | Content   | 14,849 sq.ft.      | 593,952 sq.ft.        |
| Microbevel     | 0,5 mm           | Weigh     | 18 lb              | 727 lb                |
| Joint type     | T&G              | H x W x L | 8" x 16" x 23" mm  | 43" x 32" x 79" mm    |


### DEVIATIONS:

|                           |                   |                        |
|---------------------------|-------------------|------------------------|
| Deviation on Thickness    | ± 0,2 mm          | EN 13489<br>ГОСТ 862.3 |
| Deviation on Length       | ± 0,3 mm          |                        |
| Deviation on Width        | ± 0,2 mm          |                        |
| Angle deviation of planks | ≤ 0,25 mm         |                        |
| Cup                       | ≤ 0,2 % of width  | EN 13489               |
| Bow                       | ≤ 0,5 % of length |                        |
| Spring                    | ≤ 0,1 % of length |                        |

### CHARACTERISTICS:


|                             |               |          |
|-----------------------------|---------------|----------|
| Fire resistance             | Dfl-s1        | EN 14342 |
| Formaldehyde emission class | E1            |          |
| Pentachlorophenol content   | None          |          |
| Thermal resistance          | 0,082 m2·K/W  |          |
| Thermal conductivity        | 0,161 W/(m·K) |          |
| Structural warranty         | Lifetime      |          |

### УСТАНОВКА:



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

### УСЛОВИЯ ЭКСПЛУАТАЦИИ И ХРАНЕНИЯ:



— Air humidity 40% – 65%  
 — Temperature +18 °C – +22 °C

### FINISH : SILK MAT FINISH

### GRADE : SELECT & BETTER

| DESCRIPTION:     |  | DESCRIPTION:   |  |
|------------------|--|----------------|--|
| Sound sapwood    | Non-contrasting sapwood is allowed up to 25% of plank area | Bark pocket    | Permitted up to 10 mm in length, up to 3 mm in width, filled |
| Colour variation | Permitted slight colour variation                          | Pith           | Permitted healthy heart                                      |
| Knot             | Permitted up to 10 mm, filled                              | Slope of grain | Permitted  |
| Crecks           | Not permitted  | Medullary ray  | Permitted  |

#### COSWICK Ltd.

2B Kolasa Str., 223034 Zaslavl, Republic of Belarus  
 Tel.: +375-17-543-2012, Fax: +375-17-543-2020, E-mail: sales@coswick.com  
 www.coswick.com

