




PLANK HARDWOOD FLOORING | TECHNICAL INFORMATION

Product # 1165-3888-10



WHITE BREATHE COLLECTION DECOR | CRYSTAL WHITE

Wood species | Oak
Selection | 1 Natur
Constructions | 3-layer flooring T&G
Size | 19,05x300x2950 mm (3/4"x11 13/16"x9 11/16')
Finish | Silk mat finish

CONSTRUCTION: 3-LAYER FLOORING T&G

DIMENSIONS :			PACKAGING :	
			BOX	PALLET
Thickness	19,05 mm (3/4")	Content	1,77 m2	36 box (63,72 m2)
Width	300 mm (11 13/16")	Weigh	22 kg	815 kg
Length	2950 mm (9 11/16')	H x W x L	44 x 310 x 2 955 mm	750 x 950 x 3 000 mm
Microbevel	1 mm	Content	19,045 sq.ft.	685,627 sq.ft.
Joint type	T&G	Weigh	23 lb	840 lb
Box Content: Occasional broken row consisting from 2 planks (min 600 mm) might occur in every 2nd box		H x W x L	2" x 13" x 117" mm	30" x 38" x 119" mm

DEVIATIONS:

Deviation on Thickness	± 0,2 mm	EN 13489 FOCT 862.3
Deviation on Length	- 50 mm	
Deviation on Width	± 0,2 mm	
Height Difference	≤ 0,2 mm on 100 mm length	
Cup	≤ 0,2 % of width	EN 13489
Bow	≤ 0,5 % of length	
Spring	≤ 0,1 % of length	

CHARACTERISTICS:

Fire resistance	Dfl-s1	EN 14342
Formaldehyde emission class	E1	
Pentachlorophenol content	None	
Thermal resistance	0,082 m2.K/W	
Thermal conductivity	0,161 W/(m.K)	
Structural warranty	Lifetime	

УСТАНОВКА:



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level.

УСЛОВИЯ ЭКСПЛУАТАЦИИ И ХРАНЕНИЯ:



— Air humidity 40% – 65%
 — Temperature +18 °C – +22 °C

FINISH : SILK MAT FINISH

GRADE : 1 NATUR

DESCRIPTION:		DESCRIPTION:	
Sound sapwood	Non-contrasting sapwood is allowed up to 25% of board width	Bark pocket	Not limited, restored up to 100 x 10 mm
Colour variation	Permitted slight colour variation	Pith	Permitted
Knot	Permitted up to 60 mm, filled	Slope of grain	Permitted
Crecks	Permitted wide, filled	Medullary ray	Permitted

COSWICK Ltd.

2B Kolasa Str., 223034 Zaslavl, Republic of Belarus
 Tel.: +375-17-543-2012, Fax: +375-17-543-2020, E-mail: sales@coswick.com
 www.coswick.com

