




CHEVRON 60° | TECHNICAL INFORMATION

Product # 1123-4251-20



DESIGNER SOLUTION COLLECTION DECOR | GREY CASHMERE

Wood species | Oak
Selection | Tavern
Pattern | Chevron
Constructions | 3-layer flooring T&G
Size | 19,05x127x548 mm (3/4"x5"x21 9/16")
Finish | Silk finish

CONSTRUCTION: 3-LAYER FLOORING T&G

| DIMENSIONS : | | | PACKAGING : | |
|--------------|-------------------|-----------|--------------------|-----------------------|
| | | | BOX | PALLET |
| Thickness | 19,05 mm (3/4") | Content | 1,114 m2 | 54 box (60,156 m2) |
| Width | 127 mm (5") | Weigh | 14 kg | 786 kg |
| Length | 548 mm (21 9/16") | H x W x L | 155 x 275 x 675 mm | 1080 x 832 x 2 050 mm |
| Cut angle | 60° | Content | 11,987 sq.ft. | 647,279 sq.ft. |
| Microbevel | 0,5 mm | Weigh | 15 lb | 810 lb |
| Joint type | T&G | H x W x L | 6" x 11" x 27" mm | 43" x 33" x 81" mm |

DEVIATIONS:

| | | |
|---------------------------|-------------------|------------------------|
| Deviation on Thickness | ± 0,2 mm | EN 13489 FOCT 862.3 |
| Deviation on Length | ± 0,3 mm | |
| Deviation on Width | ± 0,2 mm | |
| Angle deviation of planks | ≤ 0,25 mm | |
| Cup | ≤ 0,2 % of width | EN 13489 |
| Bow | ≤ 0,5 % of length | |
| Spring | ≤ 0,1 % of length | |

CHARACTERISTICS:

| | | |
|-----------------------------|---------------|----------|
| Fire resistance | Dfl-s1 | EN 14342 |
| Formaldehyde emission class | E1 | |
| Pentachlorophenol content | None | |
| Thermal resistance | 0,082 m2·K/W | |
| Thermal conductivity | 0,161 W/(m·K) | |
| Structural warranty | Lifetime | |

INSTALLATION :



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

STORAGE AND USAGE :



— Air humidity 40% – 65%
— Temperature +18 °C – +22 °C

FINISH : SILK FINISH

| DESCRIPTION : | |
|-----------------------|---|
| Type of coating | UV-cured modified polyurethane-acrylate |
| Surface (finish) type | Semi-closed pores, wire brushed |
| Sheen | Silk matte 9-18 GU/85° |
| Finish warranty | - |

CLASSIFICATION SURFACE CHARACTERISTICS:

| | | |
|-------------------------------|---------------------------|----------|
| Wear resistance | Not rated | EN 438-2 |
| Scratch resistance | Not rated | EN 438 |
| Slip resistance | 50 (SRV dry) | EN 15676 |
| Resistance to chemical agents | Class 5 (Except blue ink) | EN 13442 |
| Repairability | Medium | |

MAINTENANCE AND CARE CONDITIONS :

Maintenance of hardwood floors with Silk finish assumes regular (daily if necessary) cleaning from dust and grit using a vacuum, followed by a thorough cleaning with Coswick Hardwood Floor Cleaner or other similar product. Floor surface areas that receive the most traffic and get worn down quicker, such as areas by the front door, hallways, kitchens etc., should be periodically renewed with special Coswick Restorative Oil. This product restores the protective surface film. Frequency of use depends on type of interior and intensity of foot traffic. For residential interiors, restorative cleaning should be done once in 3-5 years; for public and commercial interiors with intense foot traffic, it is recommended to use the product 2-4 times a year.

SELECTION : TAVERN

| DESCRIPTION: | | DESCRIPTION: | |
|------------------|-------------------------------------|----------------|--------------------------|
| Sound sapwood | Up to 25% of board width is allowed | Bark pocket | No limit (after filling) |
| Colour variation | Moderate contrast allowed | Pith | Permitted |
| Knot | Permitted big, filled | Slope of grain | Permitted |
| Checks | Permitted wide, filled | Medullary ray | Permitted |

COSWICK Ltd.

2B Kolasa Str., 223034 Zaslavl, Republic of Belarus
Tel.: +375-17-543-2012, Fax: +375-17-543-2020, E-mail: sales@coswick.com
www.coswick.com

