




# PLANK HARDWOOD FLOORING I TECHNICAL INFORMATION

Product # 1167-1891-10



## GREY SHADOW COLLECTION DECOR | PAYNE'S GREY

**Wood species** | Oak  
**Selection** | Select & Better  
**Constructions** | 3-layer flooring T&G  
**Size** | 15x127x600...2100 mm (5/8"x5"x2'...7')  
**Finish** | Silk mat finish

### CONSTRUCTION: 3-LAYER FLOORING T&G

DIMENSIONS :			PACKAGING :	
			BOX	PALLET
Thickness	15 mm (5/8")	Content	2 m <sup>2</sup>	40 box (80 m <sup>2</sup> )
Width	127 mm (5")	Weigh	21 kg	842 kg
Length	600...2100 (2'...7')	H x W x L	128 x 160 x 2 150 mm	1136 x 810 x 2 163 mm
Average length	0.98 m (3 1/4')	Content	21,520 sq.ft.	860,800 sq.ft.
Microlevel	0,5 mm	Weigh	22 lb	854 lb
Joint type	T&G	H x W x L	5" x 7" x 85" mm	45" x 32" x 86" mm

### DEVIATIONS:

Deviation on Thickness	± 0,2 mm	EN 13489 ГОСТ 862.3
Deviation on Width	± 0,2 mm	
Height Difference	≤ 0,2 mm on 100 mm length	
Cup	≤ 0,2 % of width	EN 13489
Bow	≤ 0,5 % of length	
Spring	≤ 0,1 % of length	

### CHARACTERISTICS:

Fire resistance	Dfl-s1	EN 14342
Formaldehyde emission class	E1	
Pentachlorophenol content	None	
Thermal resistance	0,095 m <sup>2</sup> K/W	
Thermal conductivity	0,158 W/(m·K)	
Structural warranty	Lifetime	

### УСТАНОВКА:



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

### УСЛОВИЯ ЭКСПЛУАТАЦИИ И ХРАНЕНИЯ:



— Air humidity 40% – 65%  
— Temperature +18 °C – +22 °C

### FINISH : SILK MAT FINISH

### GRADE : SELECT & BETTER

DESCRIPTION:		DESCRIPTION:	
Sound sapwood	Non-contrasting sapwood is allowed up to 25% of plank area	Bark pocket	Permitted up to 10 mm in length, up to 3 mm in width, filled
Colour variation	Permitted slight colour variation	Pith	Permitted healthy heart
Knot	Permitted up to 10 mm, filled	Slope of grain	Permitted
Crecks	Not permitted	Medullary ray	Permitted

### COSWICK Ltd.

28 Kolasa Str., 223034 Zaslavl, Republic of Belarus  
Tel.: +375-17-543-2012, Fax: +375-17-543-2020, E-mail: sales@coswick.com  
[www.coswick.com](http://www.coswick.com)

