




PLANK HARDWOOD FLOORING | TECHNICAL INFORMATION

Product # 1172-3872-10



DARK WOOD COLLECTION

DECOR | PECAN

Wood species | Oak

Selection | 1 Natur

Constructions | 3-layer flooring T&G

Size | 15x190x600...2100 mm (5/8"x7 1/2"x2'...7')

Finish | Silk mat finish

CONSTRUCTION: 3-LAYER FLOORING T&G

| DIMENSIONS : | | | PACKAGING : | |
|----------------|----------------------|-----------|----------------------|-----------------------|
| | | | BOX | PALLET |
| Thickness | 15 mm (5/8") | Content | 2,26 m2 | 40 box (90,4 m2) |
| Width | 190 mm (7 1/2") | | Weigh | 23 kg |
| Length | 600...2100 (2'...7') | H x W x L | 100 x 225 x 2 165 mm | 1134 x 905 x 2 165 mm |
| Average length | 1.19 m (3 7/8') | Content | 24,318 sq.ft. | 972,704 sq.ft. |
| Microlevel | 0,5 mm | Weigh | 24 lb | 958 lb |
| Joint type | T&G | H x W x L | 4" x 9" x 86" mm | 46" x 33" x 86" mm |

DEVIATIONS:

| | | |
|------------------------|---------------------------|------------|
| Deviation on Thickness | ± 0,2 mm | EN 13489 |
| Deviation on Width | ± 0,2 mm | |
| Height Difference | ≤ 0,2 mm on 100 mm length | FOCT 862.3 |
| Cup | ≤ 0,2 % of width | EN 13489 |
| Bow | ≤ 0,5 % of length | |
| Spring | ≤ 0,1 % of length | |

CHARACTERISTICS:

| | | |
|-----------------------------|---------------|----------|
| Fire resistance | Dfl-s1 | EN 14342 |
| Formaldehyde emission class | E1 | |
| Pentachlorophenol content | None | |
| Thermal resistance | 0,095 m2 K/W | |
| Thermal conductivity | 0,158 W/(m·K) | |
| Structural warranty | Lifetime | |

УСТАНОВКА:



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

УСЛОВИЯ ЭКСПЛУАТАЦИИ И ХРАНЕНИЯ:



— Air humidity 40% – 65%
— Temperature +18 °C – +22 °C

FINISH: SILK MAT FINISH

GRADE: 1 NATUR

| DESCRIPTION: | | DESCRIPTION: | |
|------------------|---|----------------|-------------------------------------|
| Sound sapwood | Non-contrasting sapwood is allowed up to 25% of board width | Bark pocket | Permitted, restored up to 50 x 5 mm |
| Colour variation | Permitted slight colour variation | Pith | Permitted |
| Knot | Permitted up to 35 mm, filled | Slope of grain | Permitted |
| Cracks | Permitted narrow, filled | Medullary ray | Permitted |

COSWICK Ltd.

2B Kolasa Str., 223034 Zaslavi, Republic of Belarus

Tel.: +375-17-543-2012, Fax: +375-17-543-2020, E-mail: sales@coswick.com

www.coswick.com

