




PLANK HARDWOOD FLOORING | TECHNICAL INFORMATION

Product # 1135-3809-10



NATURAL TOUCH COLLECTION

DECOR | RAW SIENNA

Wood species | Oak

Selection | 1 Natur

Constructions | 3-layer flooring T&G

Size | 19,05x240x600...2100 mm (3/4"x9 1/2"x2'...7')

Finish | Silk mat finish

CONSTRUCTION: 3-LAYER FLOORING T&G

| DIMENSIONS : | | | PACKAGING : | |
|----------------|----------------------|-----------|---------------------|-----------------------|
| | | | BOX | PALLET |
| Thickness | 19,05 mm (3/4") | Content | 1,88 m2 | 36 box (67,68 m2) |
| Width | 240 mm (9 1/2") | Weigh | 24 kg | 864 kg |
| Length | 600...2100 (2'...7') | H x W x L | 90 x 275 x 2 155 mm | 1156 x 846 x 2 163 mm |
| Average length | 1.31 m (4 5/16') | Content | 20,229 sq.ft. | 728,237 sq.ft. |
| Microlevel | 0,5 mm | Weigh | 25 lb | 877 lb |
| Joint type | T&G | H x W x L | 4" x 11" x 85" mm | 46" x 33" x 86" mm |

DEVIATIONS:

| | | |
|------------------------|---------------------------|------------|
| Deviation on Thickness | ± 0,2 mm | |
| Deviation on Width | ± 0,2 mm | EN 13489 |
| Height Difference | ≤ 0,2 mm on 100 mm length | FOCT 862.3 |
| Cup | ≤ 0,2 % of width | |
| Bow | ≤ 0,5 % of length | |
| Spring | ≤ 0,1 % of length | EN 13489 |

CHARACTERISTICS:

| | | |
|-----------------------------|---------------|----------|
| Fire resistance | Dfl-s1 | |
| Formaldehyde emission class | E1 | |
| Pentachlorophenol content | None | EN 14342 |
| Thermal resistance | 0,082 m2·K/W | |
| Thermal conductivity | 0,161 W/(m·K) | |
| Structural warranty | Lifetime | |

УСТАНОВКА:



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

УСЛОВИЯ ЭКСПЛУАТАЦИИ И ХРАНЕНИЯ:



— Air humidity 40% – 65%
— Temperature +18 °C – +22 °C

FINISH: SILK MAT FINISH

GRADE: 1 NATUR

| DESCRIPTION: | | DESCRIPTION: | |
|------------------|---|----------------|-------------------------------------|
| Sound sapwood | Non-contrasting sapwood is allowed up to 25% of board width | Bark pocket | Permitted, restored up to 50 x 5 mm |
| Colour variation | Permitted slight colour variation | Pith | Permitted |
| Knot | Permitted up to 35 mm, filled | Slope of grain | Permitted |
| Cracks | Permitted narrow, filled | Medullary ray | Permitted |

COSWICK Ltd.

2B Kolasa Str., 223034 Zaslavl, Republic of Belarus

Tel.: +375-17-543-2012, Fax: +375-17-543-2020, E-mail: sales@coswick.com

www.coswick.com

