




PLANK HARDWOOD FLOORING | TECHNICAL INFORMATION

Product # 1167-1809-10



NATURAL TOUCH COLLECTION DECOR | RAW SIENNA

Wood species | Oak
Selection | Select & Better
Constructions | 3-layer flooring T&G
Size | 15x127x600...2100 mm (5/8"x5"x2'...7')
Finish | Silk mat finish

CONSTRUCTION: 3-LAYER FLOORING T&G

DIMENSIONS :			PACKAGING :	
			BOX	PALLET
Thickness	15 mm (5/8")	Content	2 m ²	40 box (80 m ²)
Width	127 mm (5")	Weigh	21 kg	842 kg
Length	600...2100 (2'...7')	H x W x L	128 x 160 x 2 150 mm	1136 x 810 x 2 163 mm
Average length	0.98 m (3 1/4')	Content	21,520 sq.ft.	860,800 sq.ft.
Microlevel	0,5 mm	Weigh	22 lb	854 lb
Joint type	T&G	H x W x L	5" x 7" x 85" mm	45" x 32" x 86" mm

DEVIATIONS:

Deviation on Thickness	± 0,2 mm	EN 13489 FOCT 862.3
Deviation on Width	± 0,2 mm	
Height Difference	≤ 0,2 mm on 100 mm length	EN 13489
Cup	≤ 0,2 % of width	
Bow	≤ 0,5 % of length	EN 13489
Spring	≤ 0,1 % of length	

CHARACTERISTICS:

Fire resistance	Dfl-s1	EN 14342
Formaldehyde emission class	E1	
Pentachlorophenol content	None	
Thermal resistance	0,095 m ² K/W	
Thermal conductivity	0,158 W/(m·K)	
Structural warranty	Lifetime	

УСТАНОВКА:



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

УСЛОВИЯ ЭКСПЛУАТАЦИИ И ХРАНЕНИЯ:



— Air humidity 40% – 65%
— Temperature +18 °C – +22 °C

FINISH : SILK MAT FINISH

GRADE : SELECT & BETTER

DESCRIPTION:		DESCRIPTION:	
Sound sapwood	Non-contrasting sapwood is allowed up to 25% of plank area	Bark pocket	Permitted up to 10 mm in length, up to 3 mm in width, filled
Colour variation	Permitted slight colour variation	Pith	Permitted healthy heart
Knot	Permitted up to 10 mm, filled	Slope of grain	Permitted
Crecks	Not permitted	Medullary ray	Permitted

COSWICK Ltd.

2B Kolasa Str., 223034 Zaslavl, Republic of Belarus
Tel.: +375-17-543-2012, Fax: +375-17-543-2020, E-mail: sales@coswick.com
www.coswick.com

