




MOSAIC WOOD FLOORS FLOORS I TECHNICAL INFORMATION

Product # 1193-3823-20



DESIGNER SOLUTION COLLECTION DECOR | SANDY

Wood species | Oak
Selection | 1 Common
Pattern | Tile
Constructions | 3-layer flooring T&G
Size | 19,05x190x220 mm (3/4"x7 1/2"x8 5/8")
Finish | Silk mat finish

CONSTRUCTION: 3-LAYER FLOORING T&G

| DIMENSIONS : | | | PACKAGING : | |
|--------------|-----------------|-----------|--------------------|-----------------------|
| | | | BOX | PALLET |
| Thickness | 19,05 mm (3/4") | Content | 1,257 m2 | 40 box (50,28 m2) |
| Width | 190 mm (7 1/2") | Weigh | 16 kg | 653 kg |
| Length | 220 mm (8 5/8") | H x W x L | 195 x 405 x 470 mm | 1113 x 800 x 1 880 mm |
| Microbevel | 0,5 mm | Content | 13,525 sq.ft. | 541,013 sq.ft. |
| Joint type | T&G | Weigh | 16 lb | 678 lb |
| | | H x W x L | 8" x 16" x 22" mm | 44" x 32" x 74" mm |

DEVIATIONS:

| | | |
|---------------------------|-------------------|------------------------|
| Deviation on Thickness | ± 0,2 mm | EN 13489 ГОСТ 862.3 |
| Deviation on Length | ± 0,3 mm | |
| Deviation on Width | ± 0,2 mm | |
| Angle deviation of planks | ≤ 0,25 mm | |
| Cup | ≤ 0,2 % of width | EN 13489 |
| Bow | ≤ 0,5 % of length | |
| Spring | ≤ 0,1 % of length | |

CHARACTERISTICS:

| | | |
|-----------------------------|---------------|----------|
| Fire resistance | Dfl-s1 | EN 14342 |
| Formaldehyde emission class | E1 | |
| Pentachlorophenol content | None | |
| Thermal resistance | 0,082 m2-K/W | |
| Thermal conductivity | 0,161 W/(m-K) | |
| Structural warranty | Lifetime | |

УСТАНОВКА:



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

УСЛОВИЯ ЭКСПЛУАТАЦИИ И ХРАНЕНИЯ:



— Air humidity 40% – 65%
 — Temperature +18 °C – +22 °C

FINISH : SILK MAT FINISH

GRADE : 1 COMMON

| DESCRIPTION: | | DESCRIPTION: | |
|------------------|---|----------------|--|
| Sound sapwood | Non-contrasting sapwood is allowed up to 25% of board width | Bark pocket | Permitted up to 50 mm in length, up to 5 mm in width, filled |
| Colour variation | Moderate contrast allowed | Pith | Permitted |
| Knot | Permitted up to 25 mm, filled | Slope of grain | Permitted |
| Crecks | Permitted narrow, filled | Medullary ray | Permitted |

COSWICK Ltd.

2B Kolasa Str., 223034 Zaslavl, Republic of Belarus
 Tel.: +375-17-543-2012, Fax: +375-17-543-2020, E-mail: sales@coswick.com
 www.coswick.com

