




# CHEVRON 60° | TECHNICAL INFORMATION

Product # 1192-3882-20



## DESIGNER SOLUTION COLLECTION DECOR | SHIBUMI

**Wood species** | Oak  
**Selection** | 1 Common  
**Pattern** | Chevron  
**Constructions** | 3-layer flooring T&G  
**Size** | 15x190x438.78 mm (5/8"x7 1/2"x17 1/4")  
**Finish** | Silk mat finish

## CONSTRUCTION: 3-LAYER FLOORING T&G

DIMENSIONS :			PACKAGING :		
			BOX	PALLET	
Thickness	15 mm (5/8")		Content	2,168 m2	30 box (65,04 m2)
Width	190 mm (7 1/2")		Weigh	22 kg	685 kg
Length	438.78 mm (17 1/4")		H x W x L	195 x 395 x 560 mm	1121 x 800 x 1 750 mm
Cut angle	60°		Content	23,328 sq.ft.	699,830 sq.ft.
Microbevel	0,5 mm		Weigh	23 lb	710 lb
Joint type	T&G		H x W x L	8" x 16" x 22" mm	45" x 32" x 69" mm

DEVIATIONS:		EN 13489 ГОСТ 862.3
Deviation on Thickness	± 0,2 mm	
Deviation on Length	± 0,3 mm	
Deviation on Width	± 0,2 mm	
Angle deviation of planks	≤ 0,25 mm	
Cup	≤ 0,2 % of width	
Bow	≤ 0,5 % of length	EN 13489
Spring	≤ 0,1 % of length	

CHARACTERISTICS:		EN 14342
Fire resistance	Dfl-s1	
Formaldehyde emission class	E1	
Pentachlorophenol content	None	
Thermal resistance	0,095 m2 K/W	
Thermal conductivity	0,158 W/(m·K)	
Structural warranty	Lifetime	

**УСТАНОВКА:**

Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

**УСЛОВИЯ ЭКСПЛУАТАЦИИ И ХРАНЕНИЯ:**

— Air humidity 40% – 65%  
 — Temperature +18 °C – +22 °C

**FINISH :** SILK MAT FINISH

**GRADE :** 1 COMMON

DESCRIPTION:		DESCRIPTION:	
Sound sapwood	Non-contrasting sapwood is allowed up to 25% of board width	Bark pocket	Permitted up to 50 mm in length, up to 5 mm in width, filled
Colour variation	Moderate contrast allowed	Pith	Permitted
Knot	Permitted up to 25 mm, filled	Slope of grain	Permitted
Crecks	Permitted narrow, filled	Medullary ray	Permitted

**COSWICK Ltd.**  
 2B Kolasa Str., 223034 Zaslavl, Republic of Belarus  
 Tel.: +375-17-543-2012, Fax: +375-17-543-2020, E-mail: sales@coswick.com  
 www.coswick.com

