




CHEVRON 60° | TECHNICAL INFORMATION

Product # 1176-3809-20



NATURAL TOUCH COLLECTION DECOR | SIENNA RUSTIC

Wood species | Oak
Selection | 1 Common
Pattern | Chevron
Constructions | 3-layer flooring T&G
Size | 15x127x548 mm (5/8"x5"x21 9/16")
Finish | Silk mat finish

CONSTRUCTION: 3-LAYER FLOORING T&G

| DIMENSIONS : | | | PACKAGING : | |
|--------------|-------------------|-----------|--------------------|-----------------------|
| | | | BOX | PALLET |
| Thickness | 15 mm (5/8") | Content | 1,392 m2 | 54 box (75,168 m2) |
| Width | 127 mm (5") | Weigh | 15 kg | 804 kg |
| Length | 548 mm (21 9/16") | H x W x L | 155 x 275 x 675 mm | 1080 x 832 x 2 050 mm |
| Cut angle | 60° | Content | 14,978 sq.ft. | 808,808 sq.ft. |
| Microbevel | 0,5 mm | Weigh | 15 lb | 828 lb |
| Joint type | T&G | H x W x L | 6" x 11" x 27" mm | 43" x 33" x 81" mm |

| DEVIATIONS: | | |
|---------------------------|-------------------|------------------------|
| Deviation on Thickness | ± 0,2 mm | EN 13489 ГОСТ 862.3 |
| Deviation on Length | ± 0,3 mm | |
| Deviation on Width | ± 0,2 mm | |
| Angle deviation of planks | ≤ 0,25 mm | |
| Cup | ≤ 0,2 % of width | EN 13489 |
| Bow | ≤ 0,5 % of length | |
| Spring | ≤ 0,1 % of length | |

| CHARACTERISTICS: | | |
|-----------------------------|---------------|----------|
| Fire resistance | Dfl-s1 | EN 14342 |
| Formaldehyde emission class | E1 | |
| Pentachlorophenol content | None | |
| Thermal resistance | 0,095 m2 K/W | |
| Thermal conductivity | 0,158 W/(m·K) | |
| Structural warranty | Lifetime | |

УСТАНОВКА:



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

УСЛОВИЯ ЭКСПЛУАТАЦИИ И ХРАНЕНИЯ:



— Air humidity 40% – 65%
— Temperature +18 °C – +22 °C

FINISH : SILK MAT FINISH

| DESCRIPTION : | |
|-----------------------|---|
| Type of coating | UV-cured modified polyurethane-acrylate |
| Surface (finish) type | Semi-closed pores, wire brushed |
| Sheen | Matte, 2-5 GU/60° |
| Finish warranty | - |

CLASSIFICATION SURFACE CHARACTERISTICS:

| | | |
|-------------------------------|---------------------------|----------|
| Wear resistance | Not rated | EN 438-2 |
| Scratch resistance | Not rated | EN 438 |
| Slip resistance | 50 (SRV dry) | EN 15676 |
| Resistance to chemical agents | Class 5 (Except blue ink) | EN 13442 |
| Repairability | Medium | |

MAINTENANCE AND CARE CONDITIONS :

Maintenance of hardwood floors with Silk finish assumes regular (daily if necessary) cleaning from dust and grit using a vacuum, followed by a thorough cleaning with Coswick Hardwood Floor Cleaner or other similar product. Floor surface areas that receive the most traffic and get worn down quicker, such as areas by the front door, hallways, kitchens etc., should be periodically renewed with special Coswick Restorative Oil. This product restores the protective surface film. Frequency of use depends on type of interior and intensity of foot traffic. For residential interiors, restorative cleaning should be done once in 3-5 years; for public and commercial interiors with intense foot traffic, it is recommended to use the product 2-4 times a year.

GRADE : 1 COMMON

| DESCRIPTION: | | DESCRIPTION: | |
|------------------|---|----------------|--|
| Sound sapwood | Non-contrasting sapwood is allowed up to 25% of board width | Bark pocket | Permitted up to 50 mm in length, up to 5 mm in width, filled |
| Colour variation | Moderate contrast allowed | Pith | Permitted |
| Knot | Permitted up to 25 mm, filled | Slope of grain | Permitted |
| Crecks | Permitted narrow, filled | Medullary ray | Permitted |

COSWICK Ltd.

2B Kolasa Str., 223034 Zaslavl, Republic of Belarus
Tel.: +375-17-543-2012, Fax: +375-17-543-2020, E-mail: sales@coswick.com
www.coswick.com

