# CHEVRON 45º I TECHNICAL INFORMATION

Product # 1175-3867-20

COSWICK
Solid Hardwood Floors



**GREY SHADOW COLLECTION**
**DECOR |** SPINEL GREY RUSTIC

**Wood species** Oak
**Selection |** 1 Common
**Pattern |** Chevron
**Constructions** 3-layer flooring T&G
**Size** |15x127x500 mm (5/8"x5"x19 11/16")
**Finish |** Silk mat finish

## CONSTRUCTION: 3-LAYER FLOORING T&G

| DIMENSIONS : | |
|---|---|
| Thickness | 15 mm (5/8") |
| Width | 127 mm (5") |
| Length | 500 mm (19 11/16") |
| Cut angle | 45° |
| Microbevel | 0,5 mm |
| Joint type | T&G |




| PACKAGING : | BOX | PALLET |
|---|---|---|
| Content | 1,27 m2 | 54 box (68,58 m2) |
| Weigh | 13 kg | 738 kg |
| H x W x L | 155 x 275 x 675 mm | 1080 x 832 x 2 050 mm |
| Content | 13,665 sq.ft. | 737,921 sq.ft. |
| Weigh | 14 lb | 762 lb |
| H x W x L | 6" x 11" x 27" mm | 43" x 33" x 81" mm |

| DEVIATIONS: | | |
|---|---|---|
| Deviation on Thickness | ± 0,2 mm | |
| Deviation on Length | ± 0,3 mm | EN 13489 |
| Deviation on Width | ± 0,2 mm | ГОСТ 862.3 |
| Angle deviation of planks | ≤ 0,25 mm | |
| Cup | ≤ 0,2 % of width | |
| Bow | ≤ 0,5 % of length | EN 13489 |
| Spring | ≤ 0,1 % of length | |

| CHARACTERISTICS: | | |
|---|---|---|
| Fire resistance | Dfl-s1 | |
| Formaldehyde emission class | E1 | |
| Pentachlorophenol content | None | EN 14342 |
| Thermal resistance | 0,095 m2 K/W | |
| Thermal conductivity | 0,158 W/(m·K) | |
| Structural warranty | Lifetime | |

**INSTALLATION :**

Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

**STORAGE AND USAGE :**




— Air humidity 40% – 65%
— Temperature +18 °C – +22 °C

## FINISH : SILK MAT FINISH

| DESCRIPTION | |
|---|---|
| Type of coating | UV-cured modified polyurethane-acrylate |
| Surface (finish) type | Semi-closed pores, wire brushed |
| Sheen | Matte, 2–5 GU/60° |
| Finish warranty | - |

| CLASSIFICATION SURFACE CHARACTERISTICS: | | |
|---|---|---|
| Wear resistance | Not rated | EN 438-2 |
| Scratch resistance | Not rated | EN 438 |
| Slip resistance | 50 (SRV dry) | EN 15676 |
| Resistance to chemical agents | Class 5 (Except blue ink) | EN 13442 |
| Repairability | Medium | |

**MAINTENANCE AND CARE CONDITIONS :**

Maintenance of hardwood floors with Silk finish assumes regular (daily if necessary) cleaning from dust and grit using a vacuum, followed by a thorough cleaning with Coswick Hardwood Floor Cleaner or other similar product. Floor surface areas that receive the most traffic and get worn down quicker, such as areas by the front door, hallways, kitchens etc., should be periodically renewed with special Coswick Restorative Oil. This product restores the protective surface film. Frequency of use depends on type of interior and intensity of foot traffic. For residential interiors, restorative cleaning should be done once in 3-5 years; for public and commercial interiors with intense foot traffic, it is recommended to use the product 2-4 times a year.

## SELECTION 1 COMMON

| DESCRIPTION: | | DESCRIPTION: | |
|---|---|---|---|
| Sound sapwood | Non-contrasting sapwood is allowed up to 25% of board width | Bark pocket | Permitted up to 50 mm in lenght, up to 5 mm in width, filled |
| Colour variation | Moderate contrast allowed | Pith | Permitted |
| Knot | Permitted up to 25 mm, filled | Slope of grain | Permitted |
| Cracks | Permitted narrow, filled | Medullary ray | Permitted |

**COSWICK Ltd.**
2B Kolasa Str., 223034 Zaslavl, Republic of Belarus
Tel.: +375-17-543-2012, Fax: +375-17-543-2020, E-mail: sales@coswick.com
**www.coswick.com**

nwfa National Wood Flooring Association
ECO FRIENDLY No added formaldehyde
CTB ISO 9001
TP BY
CE