




HERRINGBONE 90° | TECHNICAL INFORMATION

Product # 1122-1831-10



NATURAL TOUCH COLLECTION DECOR | TITANIUM BUFF

Wood species | Oak
Selection | Select & Better
Pattern | Herringbone
Constructions | 3-layer flooring T&G
Size | 19,05x127x635 mm (3/4"x5"x25")
Finish | Silk mat finish

CONSTRUCTION: 3-LAYER FLOORING T&G

| DIMENSIONS : | | | PACKAGING : | | |
|--------------|-----------------|--|-------------|--------------------|-----------------------|
| | | | BOX | PALLET | |
| Thickness | 19,05 mm (3/4") | | Content | 1,29 m2 | 54 box (69,66 m2) |
| Width | 127 mm (5") | | Weigh | 16 kg | 902 kg |
| Length | 635 mm (25") | | H x W x L | 155 x 275 x 675 mm | 1080 x 832 x 2 050 mm |
| Cut angle | 90° | | Content | 13,880 sq.ft. | 749,542 sq.ft. |
| Microbevel | 0,5 mm | | Weigh | 17 lb | 926 lb |
| Joint type | T&G | | H x W x L | 6" x 11" x 27" mm | 43" x 33" x 81" mm |

DEVIATIONS:

| | | |
|------------------------|---------------------------|------------------------|
| Deviation on Thickness | ± 0,2 mm | EN 13489 ГОСТ 862.3 |
| Deviation on Length | ± 0,3 mm | |
| Deviation on Width | ± 0,2 mm | |
| Height Difference | ≤ 0,2 mm on 100 mm length | |
| Cup | ≤ 0,2 % of width | EN 13489 |
| Bow | ≤ 0,5 % of length | |
| Spring | ≤ 0,1 % of length | |

CHARACTERISTICS:

| | | |
|-----------------------------|---------------|----------|
| Fire resistance | Dfl-s1 | EN 14342 |
| Formaldehyde emission class | E1 | |
| Pentachlorophenol content | None | |
| Thermal resistance | 0,082 m2·K/W | |
| Thermal conductivity | 0,161 W/(m·K) | |
| Structural warranty | Lifetime | |

УСТАНОВКА:



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

УСЛОВИЯ ЭКСПЛУАТАЦИИ И ХРАНЕНИЯ:



— Air humidity 40% – 65%
 — Temperature +18 °C – +22 °C

FINISH : SILK MAT FINISH

GRADE : SELECT & BETTER

| DESCRIPTION: | | DESCRIPTION: | |
|------------------|--|----------------|--|
| Sound sapwood | Non-contrasting sapwood is allowed up to 25% of plank area | Bark pocket | Permitted up to 10 mm in length, up to 3 mm in width, filled |
| Colour variation | Permitted slight colour variation | Pith | Permitted healthy heart |
| Knot | Permitted up to 10 mm, filled | Slope of grain | Permitted |
| Crecks | Not permitted | Medullary ray | Permitted |

COSWICK Ltd.

2B Kolasa Str., 223034 Zaslavl, Republic of Belarus
 Tel.: +375-17-543-2012, Fax: +375-17-543-2020, E-mail: sales@coswick.com
 www.coswick.com

