




PLANK HARDWOOD FLOORING | TECHNICAL INFORMATION

Product # 1163-7831-20



NATURAL TOUCH COLLECTION DECOR | TITANIUM BUFF RUSTIC

Wood species | Oak
Selection | Character
Constructions | 3-layer flooring T&G
Size | 19,05x190x600...2100 mm (3/4"x7 1/2"x2'...7')
Finish | Silk mat finish

CONSTRUCTION: 3-LAYER FLOORING T&G

DIMENSIONS :			PACKAGING :	
			BOX	PALLET
Thickness	19,05 mm (3/4")	Content	1,86 m ²	40 box (74,4 m ²)
Width	190 mm (7 1/2")	Weigh	23 kg	950 kg
Length	600...2100 (2'...7')	H x W x L	100 x 225 x 2 165 mm	1134 x 905 x 2 165 mm
Average length	1.22 m (4')	Content	20,014 sq.ft.	800,544 sq.ft.
Microbevel	0,5 mm	Weigh	24 lb	962 lb
Joint type	T&G	H x W x L	4" x 9" x 86" mm	46" x 33" x 86" mm

DEVIATIONS:

Deviation on Thickness	± 0,2 mm	
Deviation on Width	± 0,2 mm	EN 13489
Height Difference	≤ 0,2 mm on 100 mm length	ГОСТ 862.3
Cup	≤ 0,2 % of width	
Bow	≤ 0,5 % of length	EN 13489
Spring	≤ 0,1 % of length	

CHARACTERISTICS:

Fire resistance	Dfl-s1	
Formaldehyde emission class	E1	
Pentachlorophenol content	None	EN 14342
Thermal resistance	0,082 m ² K/W	
Thermal conductivity	0,161 W/(m·K)	
Structural warranty	Lifetime	

УСТАНОВКА:



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

УСЛОВИЯ ЭКСПЛУАТАЦИИ И ХРАНЕНИЯ:



— Air humidity 40% – 65%
— Temperature +18 °C – +22 °C

FINISH : SILK MAT FINISH

DESCRIPTION :	
Type of coating	UV-cured modified polyurethane-acrylate
Surface (finish) type	Semi-closed pores, wire brushed
Sheen	Matte, 2-5 GU/60°
Finish warranty	-

CLASSIFICATION SURFACE CHARACTERISTICS:

Wear resistance	Not rated	EN 438-2
Scratch resistance	Not rated	EN 438
Slip resistance	50 (SRV dry)	EN 15676
Resistance to chemical agents	Class 5 (Except blue ink)	EN 13442
Repairability	Medium	

MAINTENANCE AND CARE CONDITIONS :

Maintenance of hardwood floors with Silk finish assumes regular (daily if necessary) cleaning from dust and grit using a vacuum, followed by a thorough cleaning with Coswick Hardwood Floor Cleaner or other similar product. Floor surface areas that receive the most traffic and get worn down quicker, such as areas by the front door, hallways, kitchens etc., should be periodically renewed with special Coswick Restorative Oil. This product restores the protective surface film. Frequency of use depends on type of interior and intensity of foot traffic. For residential interiors, restorative cleaning should be done once in 3-5 years; for public and commercial interiors with intense foot traffic, it is recommended to use the product 2-4 times a year.

GRADE : CHARACTER

DESCRIPTION:		DESCRIPTION:	
Sound sapwood	Up to 25% of board width is allowed	Bark pocket	No limit (after filling)
Colour variation	Moderate contrast allowed	Pith	Permitted
Knot	Permitted big, filled	Slope of grain	Permitted
Crecks	Permitted wide, filled	Medullary ray	Permitted

COSWICK Ltd.

2B Kolasa Str., 223034 Zaslavi, Republic of Belarus
Tel.: +375-17-543-2012, Fax: +375-17-543-2020, E-mail: sales@coswick.com
www.coswick.com

