




# HERRINGBONE 90° | TECHNICAL INFORMATION

Product # 1171-1808-10



## WHITE BREATHE COLLECTION DECOR | VANILLA

**Wood species** | Oak  
**Selection** | Select & Better  
**Pattern** | Herringbone  
**Constructions** | 3-layer flooring T&G  
**Size** | 15x82,55x577.85 mm (5/8"x3 1/4"x22 3/4")  
**Finish** | Silk mat finish

### CONSTRUCTION: 3-LAYER FLOORING T&G

DIMENSIONS :			PACKAGING :		
			BOX	PALLET	
Thickness	15 mm (5/8")		Content	1,908 m2	54 box (103,032 m2)
Width	82,55 mm (3 1/4")		Weigh	20 kg	1094 kg
Length	577.85 mm (22 3/4")		H x W x L	155 x 345 x 620 mm	1080 x 1 065 x 2 020 mm
Cut angle	90°		Content	20,530 sq.ft.	1108,624 sq.ft.
Microbevel	0,5 mm		Weigh	21 lb	1118 lb
Joint type	T&G		H x W x L	6" x 14" x 25" mm	43" x 42" x 80" mm

### DEVIATIONS:

Deviation on Thickness	± 0,2 mm	EN 13489 ГОСТ 862.3
Deviation on Length	± 0,3 mm	
Deviation on Width	± 0,2 mm	
Height Difference	≤ 0,2 mm on 100 mm length	
Cup	≤ 0,2 % of width	EN 13489
Bow	≤ 0,5 % of length	
Spring	≤ 0,1 % of length	

### CHARACTERISTICS:

Fire resistance	Dfl-s1	EN 14342
Formaldehyde emission class	E1	
Pentachlorophenol content	None	
Thermal resistance	0,095 m2 K/W	
Thermal conductivity	0,158 W/(m·K)	
Structural warranty	Lifetime	

### УСТАНОВКА:



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

### УСЛОВИЯ ЭКСПЛУАТАЦИИ И ХРАНЕНИЯ:



— Air humidity 40% – 65%  
— Temperature +18 °C – +22 °C

### FINISH : SILK MAT FINISH

### GRADE : SELECT & BETTER

DESCRIPTION:		DESCRIPTION:	
Sound sapwood	Non-contrasting sapwood is allowed up to 25% of plank area	Bark pocket	Permitted up to 10 mm in length, up to 3 mm in width, filled
Colour variation	Permitted slight colour variation	Pith	Permitted healthy heart
Knot	Permitted up to 10 mm, filled	Slope of grain	Permitted
Crecks	Not permitted	Medullary ray	Permitted

### COSWICK Ltd.

2B Kolasa Str., 223034 Zaslavl, Republic of Belarus  
Tel.: +375-17-543-2012, Fax: +375-17-543-2020, E-mail: sales@coswick.com  
www.coswick.com

